

主要化学成分及物理性能

MAIN CHEMICAL COMPOSITION AND PHYSICAL PROPERTY

名称 Name	规格 Size	化学成分 ( % ) Chemical composition								物理性能 Physical property	
		Al <sub>2</sub> O <sub>3</sub> 不少于 Not less than	Fe <sub>2</sub> O <sub>3</sub> 不多于 Not more than	CaO 不多于 Not more than	TiO <sub>2</sub>	CaO 不多于 Not more than	Na <sub>2</sub> O 不多于 Not more than	SiC 不少于 Not less than	F.C 不多于 F.Not more than	硬度 Hardness Kg/mm <sup>2</sup>	真比重 True density g/cm <sup>3</sup>
棕刚玉微粉 A micropower	W63-W5	92.00		0.45	1.50-3.80	0.45				2000-2200	≥3.90
白刚玉微粉 WA micropower	W63-W5	98.00					0.8			2200-2400	≥3.90
	W10-W5	97.50					0.9				
绿碳化硅微粉 GC Micropower	W63-W20		0.70					97.00	0.30	3000-3300	≥3.18
	W14-W10		0.70					95.50	0.40		
	W7-W5		0.70					94.00	0.50		
黑碳化硅微粉 C Micropower	W63-W20		0.70					97.00	0.30	3000-3300	≥3.18
	W14-W10		0.70					95.50	0.40		
	W7-W5		0.70					94.00	0.50		

Zhengzhou Yue Abrasives Co., Ltd

Room 2620 Block B Wanda Plaza , Zhongyuan Disrric , Zhengzhou , Henan , China 450000

Tel:+86-371-57165510

Fax:+86-371-60224881

Website:www.yue-abrasives.com

Email:info@yue-abrasives.com



**郑州越驰**  
ZHENGZHOU YUECHI